Environmental Product Declaration In accordance with ISO 14025 and EN 15804:2012+A2:2019



П

COLORBOND® Coolmax® steel





Programme: EPD Australasia | epd-australasia.com Programme Operator: EPD Australasia Limited EPD Registration number: S-P-05199 Version 1.0 Publication date: 2023-03-23 Version date: 2023-03-23 Valid until: 2028-03-23 Geographical scope: Australia

Programme-Related Information and Verification

EPD Owner:	BlueScope Steel Ltd steeldirect@bluescopesteel.com www.bluescope.com Level 11, 120 Collins St, VIC 3000, Australia
EPD Produced by:	thinkstep-anz info@thinkstep-anz.com www.thinkstep-anz.com
Programme Operator:	EPD Australasia Ltd info@epd-australasia.com www.epd-australasia.com 315a Hardy Street, Nelson 7010, New Zealand
Product Category Rules (PCR):	PCR 2019:14 Construction Products, Version 1.11, 2021-02-05
PCR review conducted by:	The Technical Committee of the International EPD® System Chair: Claudia A. Peña Contact: info@environdec.com
Independent verification of the declaration and data, according to ISO 14025:	EPD process certification EPD verification (external)
Third party verifier:	Rob Rouwette, start2see Pty Ltd Rob.Rouwette@start2see.com.au
Verifier approved by:	EPD Australasia Ltd
Procedure for follow-up during EPD validity involves third party verifier:	☐ Yes ✔ No
Version History:	v1.0 Initial release.

General Information

- EPDs within the same product category but from different programmes may not be comparable.
- EPDs of construction products may not be comparable if they do not comply with EN 15804:2012+A2:2019 or if they are produced using different Product Category Rules (PCR).
- BlueScope Steel Limited has sole ownership, liability and responsibility for this EPD.



Hervey Bay Community Centre

Hervey Bay, Queensland

Photography: John Wilson

COLORBOND® Coolmax® steel in the colour Whitehaven®

3

Environmental Product Declaration COLORBOND® Coolmax® steel

BlueScope Steel Products

Stockland Hervey Bay Shopping Centre

To explore just how much the inclusion of micro-climate effects in energy modelling can impact predicted cool roof energy savings, BlueScope and Stockland initiated a modelling study to account for the micro-climate above a roof using a Stockland shopping centre's 15,000 square-metre roof as a reference case.

The focus of the study compared the thermal performance of roofing made from COLORBOND[®] Coolmax[®] steel in the colour Whitehaven[®], with roofing made from conventional ZINCALUME[®] steel and roofing made from COLORBOND[®] steel Surfmist[®] in a Classic finish. The study found improved thermal performance for roofing made from COLORBOND[®] Coolmax[®] steel and COLORBOND[®] steel Surfmist[®] over the roofing made from ZINCALUME[®] steel; with roofing made from COLORBOND[®] Coolmax[®] steel achieving the highest thermal performance¹.

the inclusion of micro-climate g can impact predicted cool Scope and Stockland initiated unt for the micro-climate cland shopping centre's



Stockland Hervey Bay

Hervey Bay, Queensland

Architect: PDT Architects

Photography: John Wilson

COLORBOND® Coolmax® steel in the colour Whitehaven®

Stockland

Hervey Bay

Declared Unit

This EPD provides data for one flat square metre (1 m²) of COLORBOND® Coolmax[®] steel (CMX) manufactured by BlueScope in Australia at Base Metal Thicknesses (BMTs) 0.42, 0.48 and 0.55 mm.

The product range represented by this EPD is COLORBOND® Coolmax® steel² (CMX) with a hot dipped aluminium, zinc, and magnesium alloy (AM100) coating. This EPD excludes all other COLORBOND® steel products, such as COLORBOND[®] steel for roofing and walling (XRW), COLORBOND[®] steel for garage doors, fencing, patios and pergolas and insulated panels, COLORBOND[®] steel Metallic, COLORBOND[®] Ultra steel and COLORBOND[®] Intramax[®] steel.

Key Insights

Benefits of using this EPD

This EPD can contribute to the achievement of credits under green building rating schemes. It:

Is independently verified

Includes indicators for Green Star and IS Rating

8

Product Information	16	Environmental Performance	22
Product description	16	Results for one flat square metre (1 m ²) of COLORBOND® Coolmax® steel in the following base	
Product content	17	metal thicknesses (BMTs) where the base metal is the steel:	
Scope of the declaration	19	• 0.42 mm	24
Cradle to gate (A1-A3) with modules C1-C4		• 0.48 mm	26
and module D		• 0.55 mm	28
Includes an extension of the A1 A2 seens			

Includes an extension of the A1-A3 scope to include rollforming up to the rollformer gate

BlueScope's Climate Action	10
Steel and embodied carbon	11
Achieving sustainable outcomes with steel	12

Note: EN 15804:2012+A1:2013 compliant results are also given in this document to assist comparability across EPDs and support use in tools such as Green Star and IS Rating.

Benefits of using this EPD

This EPD can contribute to the achievement of credit points under Green Star rating tools, the IS Rating Scheme (IS) and other leading green building rating schemes.

Green Star

Green Star registered projects can score points for using products with EPDs. BlueScope's steel products and this EPD may help obtain points in:

- Green Star Design and As Built v1.3
- Credit 19A Life Cycle Assessment
- Credit 19B.2 Life Cycle Impacts Steel
- Credit 20.1 Responsible Building Materials
- Credit 21 Sustainable Products
- Green Star Buildings
- Credits 6 to 9 Responsible Products (Structure, Envelope, Systems or Finishes)
- Credit 21 Upfront Carbon Emissions
- Credit 26 Life Cycle Impacts
- Green Star Communities v1.1
- Credit 26 Materials

IS Rating

IS projects can claim points for using products with EPDs. EPD results can also be included in the IS Materials Calculator and may help a project achieve reductions compared to a 'base case' footprint.

BlueScope's steel products and this EPD may help obtain points in:

- IS Design & As Built v1.2
- Mat-1 Materials Life Cycle Impact Measurement and Reduction
- Mat-2 Environmentally Labelled Products and Supply Chains
- IS Design & As Built v2.1
- Rso-6 Materials Life Cycle Impact Measurement and Reduction
- Rso-7 Sustainability Labelled Products and Supply Chains

BlueScope's products are also included in the Infrastructure Sustainability Council (ISC) ISupply Directory which connects products and services with projects and assets undertaking IS ratings.

Take care when comparing

When comparing EPDs it is important to consider:

- EPDs within the same product category but from different programmes or utilising different Product Category Rules (PCRs) may not be comparable.
- The results for EN 15804:2012+A1:2013 compliant EPDs are not comparable with EN 15804:2012+A2:2019 compliant ones, as the methodologies differ. This EPD provides additional results in accordance to EN 15804:2012+A1:2013 to assist comparability across EPDs and support use in rating tools such as Green Star and IS Rating.
- EPDs of construction products from a group of manufacturers (industry-wide EPD) may not be comparable to an EPD of a similar construction product that has been generated by a single manufacturer (product-specific or manufacturerspecific EPD).
- Understanding the detail is important in comparisons. Expert analysis is often required to understand the detail and ensure data is truly comparable, to avoid unintended distortions.
- The best way to compare products and materiality of differences is to place them into the context of a structure across the whole life cycle.

If you need help interpreting the data in this EPD, please contact BlueScope Steel Direct on 1800 800 789.

This EPD also provides:

- Environmental performance information from cradle to gate (modules A1-A3), with an extension of the A1-A3 scope to include rollforming up to the rollformer gate, plus modules C1-C4 and module D.
- · Carbon footprint data for use in Scope 3 carbon footprint calculations of your supply chain
- A wide range of environmental metrics, such as water, energy and waste

For more information on how BlueScope's products can help achieve more sustainable project outcomes contact BlueScope Steel Direct on 1800 800 789.



BlueScope's Climate Action

Steel is an essential material for modern society and a critical enabler of sustainable development. We recognise that steelmaking is emissions-intensive and we are committed to climate action. Our climate strategy outlines our decarbonisation plans, including our goal of net zero greenhouse gas emissions across our operations by 2050³, dependent on several enablers based around technology, renewable energy and public policy.

We have a promising innovation pipeline including collaborations with Rio Tinto and others, to explore ways to decarbonise iron and steelmaking processes. We believe these projects will help take us to the cutting edge of current technologies and demonstrate our commitment to reduce the embodied carbon of our products.

More information on BlueScope's climate action, can be found on our website: www.bluescope.com/sustainable-steel

OUR PATHWAY

SET A GOAL FOR: SET TARGETS FOR:



GHG emissions across our operations by 2050³



GHG emission intensity reduction by 2030 for our steelmaking activities (based on 2018 levels)



GHG emission intensity reduction by 2030 for our non-steelmaking activities⁴ (based on 2018 levels)



- The Non-Steelmaking Target applies to our midstream activities that include our cold rolled, metal coating and painting lines and long and hollow products. It excludes our downstream activities.
- 5. Pickin J et al., National Waste Report 2020, Prepared for the Department of Agriculture, Water and the Environment; 2020, p. 39.
- 6. Refers to the carbon emissions, or emissions of greenhouse gases, associated with materials throughout the life cycle of a building or infrastructure not to the carbon content in the metal allow
- 7. www.worldsteel.org/about-steel/steel-facts.html
- 8. www.iea.org/reports/iron-and-steel-technology-road



Steel and Embodied Carbon

Steel is one of the most recycled materials in the world, with the inherent value of scrap driving its recovery. In Australia, this is evidenced by a recycling rate for metals of 90%⁵. The recyclability of steel is enabled by its magnetic properties. which mean that it can be easily separated for recycling and is less likely to end up in landfill.

The recycled content in a steel product can have a significant effect on embodied carbon. While specifying high levels of recycled content can be an effective way of minimising the embodied carbon⁶ of many materials, especially those likely to be disposed of at end of life, recycled content is not necessarily a useful metric for steel in the context of reduction of carbon emissions by the steel sector. This is because despite being one of the most recycled materials in the world7, there is not enough steel scrap available to meet the growing global demand for steel⁸.

Specification of 'secondary' steel or steel products with higher levels of recycled content as a means of reducing embodied carbon, is unlikely to cause more steel to be recycled. Rather, doing so may shift the environmental burden around the value chain, and in fact increase the burden, as scrap and the final product may be transported around the globe unnecessarily.

While global demand for scrap continues to outstrip supply, the development and deployment of new low GHG emissions technologies for 'primary' steel production (using raw material inputs such as iron ore and metallurgical coal) while increasing the role of 'secondary' steelmaking (principally using scrap steel), will be key to reducing carbon emissions in the steel sector.

Embodied carbon and climate transition in a hard-to-abate sector

There is growing recognition from research and standard setting organisations that the percentage of recycled content in steel is not a good proxy for climate transition for the steel sector.

New methodologies, tools and guidance are being developed by organisations such as ResponsibleSteel[™], to enable steel companies to set targets that align with science-based decarbonisation pathways and consider the unique context of the sector.

BlueScope is a participant in the Expert Advisory Group convened by the Science Based Targets initiative (SBTi) for the development of science-based target setting methodologies, tools and guidance in the steel sector to help meet the 1.5 °C goal of the Paris Agreement.

These initiatives build on the work of the Net Zero Steel Pathway Methodology Project (NZSPMP), which developed recommendations to identify and recognise low carbon emissions steelmaking, irrespective of the proportion of scrap or iron ore used as the primary input material. This approach would enable users to identify and reward reductions in embodied carbon and efficiencies in manufacturing practices for the steel sector, rather than simply identifying products that use more or less scrap steel, creating the basis for downstream users of steel to contribute to the achievement of the Paris Agreement through their steel specifying and purchasing decisions, and to recognise responsible steelmakers for their own commitment.

More information: www.sciencebasedtargets.org/sectors/steel and www.netzerosteelpathwayproject.com

Responsible Steel |standards & certification

BlueScope is a founding member of ResponsibleSteel[™], the steel industry's first global multi-stakeholder standard and certification program. It has been designed to ensure customers, stakeholders and consumers can be confident that the steel they use has been sourced and produced responsibly.

Initiatives, such as ResponsibleSteel™. are incorporating new methodologies to ensure that the carbon emissions of steel products are calculated on a like-for-like basis, irrespective of the input materials used and the steel production technology.

Achieving Sustainable Outcomes with Steel

Steel is central to a circular economy – one where resources and materials are kept in use for as long as possible and then repaired, returned or recycled. Steel can be infinitely recycled and is 100% recyclable without loss of quality.

Design considerations

Life cycle thinking. A focus on design is important to minimise the whole of life impact of any construction project. Steel is a strong, durable and versatile material. It lends itself well to structures that are designed for long life, resilience and flexibility to accommodate multiple future reuse options without reinvestment in structural alteration and refurbishment. Steel also supports designs where end of life considerations are key e.g. designing for disassembly and reuse.

Dematerialisation. BlueScope manufactures a range of standard and high strength steel grades in plate and coil form. High strength steel grades enhance the strength to weight performance in structural steel applications when the design is governed by strength; by maximising the strength grade, a reduced volume of steel would be required in these applications, e.g. columns and primary members. This in turn can result in embodied carbon savings relative to a reference building design that utilises standard steel grades.

Specification considerations

ResponsibleSteel[™]. ResponsibleSteel[™] is the steel industry's first global multi-stakeholder standard and certification initiative. The ResponsibleSteel[™] Standard covers a wide range of sustainability topics, including Climate Change and Greenhouse Gas Emissions, Biodiversity, Water Stewardship and Human Rights. Specifying steel from a ResponsibleSteel[™] certified site supports steel manufacturers such as BlueScope who are committed to climate action and sustainability. It also supports those downstream to manage ESG (Environmental, Social and Governance) risks in the steel supply chain.

More information: www.responsiblesteel.org

EPDs and ecolabels. EPDs and ecolabels demonstrate a manufacturer's commitment to product transparency and stewardship. EPDs and ecolabels provide key sustainability information to support decision-making and the achievement of more sustainable outcomes.

Further information on the sustainability credentials of BlueScope's products: www.steel.com.au

Manufacturer commitments and investment. Understand the commitments manufacturers have made to sustainability and climate change action and consider their investment in Research & Development activities.

More information on BlueScope's commitments and activities can be found in our Climate Action Report and Sustainability Report: www.bluescope.com/sustainable-steel/reports/



Bulli Hospital and Aged Care Centre Bulli, New South Wales Architect: Billard Leece Partnership

COLORBOND® Coolmax® steel in the colour Whitehaven®

Contributing to a Sustainable Future

BlueScope has a long-standing commitment to developing innovative, responsible products and services. You can design and specify with confidence, knowing that COLORBOND® Coolmax® steel (CMX) is created with durability, performance, compliance and sustainability top of mind.

Steel and the Circular Economy

Steel is strong, durable, and versatile and its inherent properties allow it to be recycled without loss of quality over and over again. In some cases, it can be reused without reprocessing, again saving on energy and resource use.

To help support a more sustainable 'circular economy', the steel manufactured by BlueScope in Australia incorporates pre- and post-consumer recycled content⁹. Steel is 100% recyclable and its magnetic properties mean that it can be easily separated for recycling and is less likely to end up in landfill.

Durable and Resilient

All COLORBOND® steel products, including COLORBOND® Coolmax® steel, are tried and tested in Australian conditions to look great and deliver outstanding, long life performance. COLORBOND® Coolmax® steel is durable and resilient to Australia's harsh climate and incorporates BlueScope's industry-leading metallic coating, incorporating Activate® technology, to provide enhanced corrosion resistance. Its long life can help conserve resources and energy that may otherwise be invested in products with shorter life spans.

Thermal Performance

Available exclusively in the colour Whitehaven®, COLORBOND® Coolmax® steel is a roofing product designed to provide and maintain high solar reflectance with a nominal solar reflectance value¹⁰ of 0.77 which means it reflects 77% of the sun's heat, which can help to reduce roofing temperatures and keep the building cooler¹¹. Using COLORBOND® Coolmax® steel may help reduce building energy costs and upfront air conditioning equipment costs¹². In addition, COLORBOND® Coolmax® steel can help mitigate the impact of urban heat islands.

COLORBOND® Coolmax® steel in the colour Whitehaven® meets the National Construction Code 'deemed to satisfy' solar absorptance requirements for commercial roofing, as well as the Green Star rating Solar Reflectance Index (SRI) benchmark for the Heat Island Effect and Heat Resilience credits.

For more information about COLORBOND® Coolmax® steel visit www.steel.com.au

Stockland Hervey Bay

Hervey Bay, Queensland

Architect: **PDT** Architects

Photography: John Wilson

COLORBOND[®] Coolmax steel in the colour Whitehaven[®]

Warranty Confidence

When you specify, purchase or install COLORBOND® Coolmax® steel you are also benefiting from the support of BlueScope, one of Australia's largest manufacturers. COLORBOND® Coolmax® steel is renowned for its durability, and is backed by BlueScope. BlueScope offers a variety of warranties subject to application and eligibility criteria.13

- 9. Across the range of steel products manufactured by BlueScope in Australia, the average recycled content (according to recycled content categories defined in ISO 14021:2016) in the steel is 17.4%, which includes pre- and post-consumer recycled materials. Scrap and iron-bearing materials generated and reclaimed from BlueScope's steelmaking, coating and painting operations represent an additional 6.8% recovered content, which is not reported as recycled content. Scrap from rollforming and fabrication processes are included as pre-consumer recycled content. The figures provided represent our best estimate at the time of publication. For current recycled content figures please contact BlueScope Steel Direct on 1800 800 789.
- 10. Nominal values based on new product. Solar Reflectance is measured in accordance with ASTM E 903-96, standard test method for solar absorptance, reflectance and transmittance of materials using integrating spheres. SRI determined in accordance with ASTM E1980-11.
- 11. Compared to conventional roofing materials of lower reflectance index (SRI), such as ZINCALUME[®] steel and all other roofing materials in the COLORBOND[®] steel range. Any savings and or the extent to which a building is cooler may vary and depend upon the particular circumstances of the building, including building location, level of insulation, location of air-conditioning when installed, building shape building function and environmental factors.

12. For more information refer to the COLORBOND® Coolmax® steel Arup Summary Report: Microclimate Study and the BlueScope Microclimate Thermal Study Stage 1a Microclimate Study ARUP at www.steel.com.au/library. For more information about potential savings visit www.steel.com.au/cool 13. Warranties subject to exclusions, application, and eligibility criteria. For full terms and conditions visit www.bluescopesteel.com.au/warranties





Certification of Port Kembla Steelworks

BlueScope's Port Kembla Steelworks is certified to the ResponsibleSteel[™] Standard version 1.1. Australia's largest steel production facility has an annual production capacity of approximately 3 million tonnes of crude steel.

It manufactures slab, hot rolled coil and plate products. Branded products such as COLORBOND® Coolmax[®] steel, COLORBOND[®] steel, TRUECORE[®] steel, ZINCALUME® steel and XLERPLATE® steel are manufactured from steel produced at the Port Kembla Steelworks.

Declared Unit

This EPD is valid for one flat square metre (1 m²) of COLORBOND® Coolmax® steel (CMX) manufactured by BlueScope in Australia.

Product Description

COLORBOND® Coolmax® steel (CMX) is BlueScope's roofing material designed to provide and maintain high solar reflectance. COLORBOND® Coolmax[®] steel, available exclusively in the colour Whitehaven[®], is specifically designed to provide low solar absorptance to help reduce roofing temperatures. Typical COLORBOND® Coolmax® steel applications are for commercial and industrial roofing.

This EPD sets out information on the average COLORBOND® Coolmax® steel (CMX) product¹⁴ manufactured by BlueScope in Australia, in the base metal thicknesses (BMTs) presented in the table below.

The product range represented by this EPD only includes COLORBOND® Coolmax® steel (CMX) with a hot dipped aluminium, zinc, and magnesium alloy (AM100) coating, in the colour Whitehaven®. It excludes all other COLORBOND® steel products, such as COLORBOND® steel for roofing and walling (XRW), COLORBOND[®] steel for garage doors, fencing, patios and pergolas and insulated panels, COLORBOND® steel Metallic, COLORBOND® Ultra steel and COLORBOND® Intramax® steel. This EPD also excludes removable films that may be applied to COLORBOND® Coolmax® steel at the paint line for protection during transport and installation.

The COLORBOND® Coolmax® steel products represented in this EPD consist of a low carbon¹⁵ steel substrate that is coated with a metallic coating incorporating BlueScope's Activate® technology (hot dipped aluminium, zinc, and magnesium alloy AM100 coating) to provide enhanced corrosion resistance, and then further protected and enhanced with a specially developed, exterior-grade, oven-baked paint system designed specifically for high solar reflectance.

The metallic coated base steel (G300S or G550S strength grade), conforms to AS 1397:2021 Continuous hot-dip metallic coated steel sheet and strip -Coatings of zinc and zinc alloyed with aluminium and magnesium.

The paint system meets the performance requirements of AS/NZS 2728:2013 Prefinished/pre painted sheet metal products for interior/exterior building applications - Performance requirements.

Product	Metallic Coating	Base Metal Thickness (BMT)	Product mass (kg/m² flat product)		
COLORBOND® Coolmax [®] steel		0.42 mm	3.48		
	AM100	0.48 mm	3.95		
		0.55 mm	4.50		

Manufacturing Process

In Australia, BlueScope manufactures steel from raw and recycled materials using an 'integrated steelmaking' method. This involves the use of iron ore, coal, steel scrap, fluxes (limestone and dolomite) and alloying materials to produce steel slab via the major processes of sintering, coke making, Blast Furnace/Basic Oxygen Furnace (BF-BOF) steelmaking and continuous slab casting, prior to hot rolling into hot rolled coil steel.

The hot rolled coil is then cold reduced. Cold reduction involves pickling (acid cleaning) the coil, followed by cold rolling, where the steel coil is compressed and elongated through rolls to reduce its thickness and increase the strength of the steel. Following cold reduction, the coil is annealed to the required strength, metallic coated for corrosion resistance and skin passed for improved surface finish at the continuous hot-dipped metal coating lines. The metallic coated coil is then transferred to a paint line, where pre-treatment, primer, finish and reverse coat layers are baked on to produce the COLORBOND® Coolmax® steel product prior to recoiling and packaging ready for shipment to customers for processing.

Downstream processing

COLORBOND® Coolmax® steel (CMX) is supplied by BlueScope to downstream processors in coils. These coils are un-coiled and formed into roofing profiles. The finished products are delivered to construction sites for installation. A wide variety of attractive profiles with different spanning strengths, fixing methods and visual aesthetics are produced.

To provide indicative results for the final formed product up to the rollforming gate, data has been obtained from selected sites of several rollformers based in Australia, including Lysaght (all sites), Metroll (Perth, Albany and Bunbury sites) and Steeline (Hunter sites). These results are presented as 'A1-A3 incl. rollforming' in the Results section. The indicative rollforming results represent an average of the data collected from the surveyed sites only¹⁶. These results may not be representative of the final formed product from any particular rollforming operation, company or site. Actual results will vary depending on a range of factors specific to the particular operations of the downstream processors.



Product Content

The average composition¹⁷ of one flat square metre (1 m²) of COLORBOND[®] Coolmax[®] steel (CMX) is:

Product composition		Mass (kg)	Recycled material (pre- and post-consumer)				
Steel Substrate	te Carbon Steel 3.30 (0.42 m 4.32 (0.55 n		17.4% (average recycled content in the steel manufactured by BlueScope in Australia) ¹⁸				
	Aluminium	0.049-0.059	-				
	Magnesium	0.001-0.003	-				
Metallic Coating	Silicon	0.001-0.002	-				
	Zinc	0.040-0.053	-				
Paint Coatings	Topcoat ¹⁹	0.07	-				
	Backing coat ²⁰	0.02	-				

Packaging Materials	Mass (kg)	Packaging (as % of product mass)
Steel	0.012	0.27%-0.34%
Plastic (excl. CORSTRIP® film/strippable film ²¹)	0.002	0.04%-0.06%
Cardboard	0.001	0.02%-0.03%
Timber	0.007	0.16%-0.20%

COLORBOND® Coolmax® steel (CMX) is compliant with the European REACH regulation²². For safe use and maintenance information, refer to the product Safety Data Sheet (SDS) at www.steel.com.au/library.

What is an SDS?

A Safety Data Sheet (SDS) is a document that describes the chemical and physical properties of a product or material and provides safe handling and use information.

Industry Classification

Product	Classification	Code
COLORBOND® Coolmax®	UN CPC	41231
steel (CMX)	ANZSIC	2110

17. The product composition provided is an average and variability among invididual products is expected. Please note that we are constantly working to improve our products and changes to their composition may occur over time. If clarification on a particular product is needed please contact BlueScope Steel Direct on 1800 800 789.

18. Across the range of steel products manufactured by BlueScope in Australia, the average recycled content (according to recycled content categories defined in ISO 14021:2016) in the steel is 17.4%, which includes pre- and post-consumer recycled materials. Scrap and iron-bearing materials generated and reclaimed from BlueScope's steelmaking, coating and painting operations represent an additional 6.8% recovered content, which is not reported as recycled content. Scrap from rollforming and fabrication processes are included as pre-consumer recycled content. The figures provided represent our best estimate at the time of publication. For current recycled content figures please contact BlueScope Steel Direct on 1800 800 789.

19. Proprietary coatings (pre-treatment, primer and finish coat).

20. Proprietary coatings (pre-treatment, primer and reverse coat).

15. The term 'low carbon steel' refers to the carbon content in the metal alloy (which is typically less than 0.3% carbon content), and not to the carbon dioxide (CO2) emissions associated with the product 16. Results are based on rollforming data corresponding to a 12 month period, which varied by rollformer (ranging from July 2018 to June 2021). Some of this data has been obtained from third parties.

14. Refer to the COLORBOND® Coolmax® steel (CMX) datasheet at www.steel.com.au

22, Regulation (EC) No. 1907/2006 of the European Parliament and of the Council of 18 December 2006 on the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH).

Category
Flat-rolled products of non-alloy steel, clad, plated, coated or otherwise further worked
Iron Smelting and Steel Manufacturing

21. Some COLORBOND® Coolmax® steel products are delivered with CORSTRIP® film to protect the product from damage during transport and installation. CORSTRIP® film is made from 100% low-density polyethylene (LDPE). Note occasionally strippable film may be supplied in lieu of CORSTRIP® film for operational reasons.



COLORBOND[®] Coolmax[®] steel **Manufacturing and Processing** in Australia



Scope of Declaration

This declaration is for one flat square metre (1 m²) of COLORBOND[®] Coolmax[®] steel (CMX) manufactured by BlueScope in Australia²⁴. The scope of this declaration is from cradle to gate (modules A1-A3), with modules C1-C4 and module D. It includes an extension of the modules A1-A3 to include rollforming up to the rollformer gate²⁵.

Modules A4-A5 (construction process) and B1-B7 (use) have not been included due to the inability to predict how the material will be used following manufacture.

The system boundary applied in this study extends from mining of raw materials such as iron ore and coal; transport to and within the manufacturing site; coke, sinter, iron and steel manufacture; ancillary service operations; hot rolling of steel products, cold reduction, metallic coating and coil painting and packaging for dispatch to direct customers at the exit gate of the paint line. Removable films that may be applied to COLORBOND® Coolmax® steel at the paint line for protection during transport and installation are excluded from the scope of this EPD.

The system boundary has been extended to include transport to the rollforming site, rollforming operations and packaging for dispatch to rollformers' customers at the exit gate of the rollforming site, presented as 'A1-A3 incl. rollforming' in the Results section.

The system boundary also includes manufacture of other required input materials, transport between processing operations, the production of external services such as electricity, natural gas and water, and the production of co-product materials within the steelmaking process, which have been removed by the use of allocation techniques. Wastes and emissions to air, land and water are also included, as are modules C1-C4 (end of life stage), and module D (reuse, recovery and/or recycling potential).

	Product stage Construction process stage				Use stage					End of life stage			Benefits and loads beyond the system boundary				
	Raw material supply	Transport	Manufacturing	Transport	Construction / installation	Use	Maintenance	Repair	Replacement	Refurbishment	Operational energy use	Operational water use	De-construction, demolition	Transport	Waste processing	Disposal	Reuse / recovery / recycling potential
Modules	A1	A2	A3	Α4	A5	B1	B2	В3	B4	B5	B6	B7	C1	C2	СЗ	C4	D
Modules declared	Х	х	х	ND	ND	ND	ND	ND	ND	ND	ND	ND	х	х	х	х	Х
Geography	AU	AU	AU	-	-	-	-	-	-	-	-	-	AU	AU	AU	AU	GLO
Specific data		>90%	,	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Variation - products		<10%		-	-	-	-	-	-	_	-	-	-	-	-	-	_
Variation - sites		<10%		-	-	-	-	-	-	-	-	-	-	-	-	-	_

X = Module declared; ND = Not declared (such a declaration shall not be regarded as an indicator of a zero result)

23. Results inclusive of the rollforming process are presented as 'A1-A3 incl. rollforming' in the Results section. 24. As described in the Product Description on page 16.

25. To provide indicative results for the final formed product up to the rollforming gate, data has been obtained from selected sites of several rollformers based in Australia. Results are based on rollforming data corresponding to a 12 month period, which varied by rollformer (ranging from July 2018 to June 2021). The results represent an average of the data from the surveyed sites only. These results may not be representative of the final formed product from the rollforming operations of other companies or sites. Actual results will vary depending on a range of factors specific to the particular operations of the downstream processors. Some of this data has been obtained from third parties. BlueScope does not accept any responsibility for the accuracy, completeness or reliability of data provided by third parties

Life Cycle Assessment (LCA) Methodology

This EPD has been produced in conformance with the requirements of PCR 2019:14 v1.11 Construction Products, the Instructions of the Australasian EPD Programme v3.0, and the International EPD® System General Programme Instructions (GPI) v3.01.

Primary data

This study focuses on the further processing of steel beyond hot rolling to produce COLORBOND® Coolmax® steel (CMX). Upstream hot rolled steel manufacturing data for low carbon²⁶ Hot Rolled Coil used in this study was obtained from v2.0 of the EPD for Steel - Hot Rolled Coil (S-P-00557).

Primary data were collected for all relevant BlueScope manufacturing sites in Australia, for all inputs and outputs in the production stage (A1-A3). This study is based on an annual average for the time period July 2018 to June 2019. All direct emissions data were procured from the average results reported to the National Pollution Inventory over the 3-year period 2016 to 2019.

To provide indicative results for the final formed product up to the rollforming gate, primary data for roll forming were collected from selected sites of several rollformers based in Australia. including Lysaght (all sites), Metroll (Perth, Albany and Bunbury sites) and Steeline (Hunter sites). The data was collected across a 12 month period ranging from July 2018 to June 2021 for each site.

Secondary data

The secondary data used were procured from the GaBi Life Cycle Inventory Database 202227. Most datasets used have a reference year between 2018 and 2021 and all fall witihn the 10-year limit allowable for generic data under EN 15804.

For the modelling for BlueScope's manufacturing sites, the electricity supply was based on GaBi's state-specific 1kV-60kV grid mix datasets for NSW and VIC as relevant to each BlueScope manufacturing site.

The 2019 1kV-60kV NSW grid mix dataset is highly reliant on hard coal (77%), with imports from VIC (6.5%) and QLD (5.6%), and generation from hydro (4.1%), natural gas (3.3%), wind (2.5%) and photovoltaics (0.74%). The emission factor for the 2019 1kV-60kV NSW grid for the GWP-GHG indicator is 0.987 kg CO₂-eq./kWh (GaBi database 2022).

The 2019 1kV-60kV VIC grid mix dataset is highly reliant on lignite (80%), with generation from hydro (6.3%), wind (6.2%), and natural gas (3.2%), and imports from TAS (2.4%), NSW (1.1%) and SA (0.68%). The emission factor for the 2019 1kV-60kV VIC grid for the GWP-GHG indicator is 1.13 kg CO2-eq./kWh (GaBi database 2022).

For the modelling for rollforming operations, the GaBi statespecific grid mix datasets were used to create a productionweighted average grid mix, based on BlueScope's transport data to rollformers in different States, resulting in an emission factor for the GWP-GHG indicator of 0.942 kg CO₂-eq./kWh.

Water use in relation to BlueScope's manufacturing sites was modelled using the specific watershed scarcity data for each BlueScope manufacturing site. For the rollforming operations, water use was modelled using the generic Australian water scarcity data for rollforming.

Cut off criteria

All relevant and available data were collected. While cut-off criteria according to the Product Category Rules (PCR) section 4.4 were employed, much of the data which would have fallen within that scope were included where available, resulting in a data set which is robust and captures all significant contributors to the LCA results. Inputs knowingly excluded are the transport and packaging of minor inputs, such as lubricants and greases, which are used in very small quantities.

Personnel is excluded as per section 4.3.1 in the PCR (EPD International, 2021). thinkstep-anz consistently excludes environmental impacts from infrastructure, construction, production equipment, and tools that are not directly consumed in the production process ('capital goods'). This is because high-quality infrastructure-related data isn't always available and there is no clear cut-off for what to include. For this reason, capital goods data may be applied to LCA studies inconsistently and could lead to reduced consistency and comparability of EPDs. Capital goods were excluded from previous EPDs. thus including capital goods in this current EPD could further reduce comparability.

Allocation

Where subdivision of processes was not possible, allocation was carried out using the most relevant physical quantity, predominantly the mass of throughput (e.g. steel coil) or surface area of the coil (e.g. surface coatings). Economic allocation was not used in this study. No use of system expansion was made (excepting Module D).

End of life

The modelling for Module C1 was based on the use of a 100 kW construction excavator (fuel consumption of 0.172 kg diesel per tonne steel). The modelling for Module C2 assumed 50 km transport by truck to waste processing facility or landfill.

The recycling scenario was based on the National Waste Report 2020²⁸, which indicates that the average metals recycling rate in Australia is 90%. This is considered to be a conservative estimate for flat steel construction products but was used in the absence of verified higher recycling rates.

End of life allocation follows the requirements of EN 15804:2012+A2:2019 section 6.4.3.3 and generally follows the polluter pays principle. Any open scrap inputs into manufacturing remain unconnected, and so are treated as 'burden free'. At the end of life of a product, scrap is collected for recycling and is thus available to produce a recycling credit within Module D. A credit for net scrap is given in Module D based on the base metal used in the product.

Key assumptions and qualifications:

- · Accuracy of data measurement falls within normal industrial weighing systems accuracy limits of +/-5%.
- Transport and packaging of minor materials is insignificant to the overall impacts.
- · Nominally identical products are produced on a combination of production lines in parallel, and therefore the impacts of each product are a weighted average of the various production lines. The impact of any differences in the composition of the products, with the exception of any change in base metal thickness (BMT), is insignificant on the outcomes of the LCA.
- Proprietary chemicals and paints can be sufficiently modelled using guidance from Safety Data Sheets and conservative assumptions on that basis.
- Upstream data taken from the GaBi LCI database reflects average or generic production and therefore does not correspond to BlueScope's actual suppliers.
- · Rollforming data has been obtained from selected sites of several rollformers based in Australia. Some of this data has been obtained from third parties. BlueScope does not accept any responsibility for the accuracy, completeness or reliability of data provided by third parties. The rollforming results may not be representative of the final formed product from any particular rollforming operation, company or site. Actual results will vary depending on a range of factors specific to the particular operations of the downstream processors.
- The Module D recovery stage assumes that paint coatings are incinerated and metal coatings are lost as slag during the steel recycling process. This is a conservative assumption for metal coatings as they are likely to make up part of future steel alloys.



Environmental Performance

The environmental impact indicators included in this EPD are described in the table below. All the result tables from this point will contain the abbreviations only. All results reported in MJ are in net calorific value.

Indicator	Abbreviation	Units	Characterisation Method
Core Environmental Impact indicators, in accordance to EN 15804:2012	+A2:2019		
Climate change – total	GWP-total	kg CO₂-eq.	EF3.0 (PEF)
Climate change – fossil	GWP-fossil	kg CO₂-eq.	EF3.0 (PEF)
Climate change – biogenic	GWP-biogenic	kg CO₂-eq.	EF3.0 (PEF)
Climate change – land use and land use change	GWP-luluc	kg CO₂-eq.	EF3.0 (PEF)
Ozone depletion	ODP	kg CFC-11-eq.	WMO 2014
Acidification	AP	mol H⁺-eq.	Accumulated Exceedance
Eutrophication aquatic freshwater	EP-freshwater	kg P-eq.	EUTREND model (ReCiPe)
Eutrophication aquatic marine	EP-marine	kg N-eq.	EUTREND model (ReCiPe)
Eutrophication terrestrial	EP-terrestrial	mol N-eq.	Accumulated Exceedance
Photochemical ozone formation	POCP	kg NMVOC-eq.	LOTOS-EUROS
Depletion of abiotic resources – minerals and metals	ADP-minerals & metals	kg Sb-eq.	CML 2002a
Depletion of abiotic resources – fossil fuels	ADP-fossil	MJ	CML 2002a
Water depletion potential	WDP	m ³ world-eq. deprived	AWARE
Additional Environmental Impact indicators, in accordance to EN 15804	:2012+A2:2019		
Climate change	GWP-GHG	kg CO₂-eq.	IPCC 2013 (AR5)
Particulate Matter emissions	PM	Disease incidence	SETAC-UNEP, Fantke et al. 2016
Ionising radiation – human health	IRP	kBq U-235-eq.	Human Health Effect model
Eco-toxicity – freshwater	ETP-fw	CTUe	Modified USEtox model from EC-JRC
Human toxicity potential – cancer effects	HTP-c	CTUh	Modified USEtox model from EC-JRC
Human toxicity potential – non-cancer effects	HTP-nc	CTUh	Modified USEtox model from EC-JRC
Land use related impacts / soil quality	SQP	dimensionless	Soil quality index (LANCA®)
Resource use parameters			
Use of renewable primary energy excluding renewable primary energy resources used as raw materials	PERE	MJ	n/a
Use of renewable primary energy resources used as raw materials	PERM	MJ	n/a
Total use of renewable primary energy resources	PERT	MJ	n/a
Use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials	PENRE	MJ	n/a
Use of non-renewable primary energy resources used as raw materials	PENRM	MJ	n/a
Total use of non-renewable primary energy resources	PENRT	MJ	n/a
Use of secondary material	SM	kg	n/a
Use of renewable secondary fuels	RSF	MJ	n/a
Use of non-renewable secondary fuels	NRSF	MJ	n/a
Net use of fresh water	FW	m ³	n/a

Waste Categories and Output Flows			
Hazardous waste disposed	HWD	kg	n/a
Non-hazardous waste disposed	NHWD	kg	n/a
Radioactive waste disposed	RWD	kg	n/a
Components for re-use	CRU	kg	n/a
Materials for recycling	MFR	kg	n/a
Materials for energy recovery	MER	kg	n/a
Exported energy – electrical	EEE	MJ	n/a
Exported energy - thermal	EET	MJ	n/a
Additional Environmental Impact indicators, in accordance to EN	15804:2012+A1:2013	·	'
Global warming potential	GWP	kg CO₂-eq.	IPCC 2007 (AR4)
Ozone depletion potential	ODP	kg CFC-11-eq.	WMO 2003
Acidification potential	AP	kg SO₂-eq.	CML 2002b
Eutrophication potential	EP	kg PO₄³eq.	CML 2002b
Photochemical ozone creation potential	POCP	kg C₂H₄-eq.	CML 2002b
Abiotic depletion potential for non-fossil resources	ADPE	kg Sb-eq.	CML 2002b
Abiotic depletion potential for fossil resources	ADPF	MJ	CML 2002b
Additional Green Star v1.3 indicators		·	'
Human Toxicity – cancer effects	HTc - GS	CTUh	USEtox
Human Toxicity - non-cancer effects	HTnc - GS	CTUh	USEtox
Land use	LU - GS	kg C deficit-eq.	Soil Organic Matter method
Resource depletion – water	RDW - GS	m³-eq.	Water Stress Indicator
Ionising radiation	IR – GS	kBq U235-eq.	Human Health Effect model
Particulate matter	PM - GS	kg PM2.5-eq.	RiskPoll

Results for 1 m² of COLORBOND[®] Coolmax[®] steel in 0.42mm base material thickness (BMT)

In accordance to EN 15804:2012+A2:2019

Product mass: 3.48 kg/m² flat

Note: Results for 'A1-A3 incl. rollforming' are for one square metre (1 m²) of flat product. The profile of the rollformed roofing product will affect how many flat square metres are required to cover a given surface area.

Environmental Impacts

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	СЗ	C4	D
GWP-total	kg CO ₂ -eq.	12.1	12.4	0.00218	0.0165	0.153	0.0169	-4.34
GWP-fossil	kg CO ₂ -eq.	12.1	12.5	0.00217	0.0165	0.153	0.0168	-4.34
GWP-biogenic	kg CO ₂ -eq.	-0.0102	-0.100	2.15E-07	5.50E-06	1.71E-04	3.32E-05	0.00253
GWP-luluc	kg CO ₂ -eq.	4.68E-04	8.90E-04	1.58E-08	1.78E-07	5.88E-06	1.01E-05	-8.87E-05
ODP	kg CFC-11-eq.	6.71E-12	7.44E-12	1.73E-16	1.66E-15	6.82E-13	2.21E-14	6.82E-14
AP	mol H⁺-eq.	0.0425	0.0442	1.03E-05	4.26E-05	7.71E-04	5.31E-05	-0.00431
EP-freshwater	kg P-eq.	3.31E-06	4.43E-06	3.82E-10	2.71E-09	8.38E-08	1.29E-08	-7.75E-07
EP-marine	kg N-eq.	0.00935	0.00979	4.99E-06	1.92E-05	1.65E-04	1.29E-05	-3.23E-04
EP-terrestrial	mol N-eq.	0.105	0.109	5.47E-05	2.12E-04	0.00180	1.42E-04	1.79E-04
POCP	kg NMVOC-eq.	0.0314	0.0327	1.40E-05	4.11E-05	4.58E-04	4.09E-05	-0.00306
ADP-minerals & metals ²⁹	kg Sb-eq.	3.02E-05	3.08E-05	2.65E-11	2.97E-10	1.29E-08	1.17E-09	-2.19E-07
ADP-fossil ²⁹	MJ	123	129	0.0289	0.219	1.66	0.239	-39.4
WDP ²⁹	m ³ world-eq. deprived	0.777	0.838	1.61E-05	1.04E-04	0.0599	0.00114	-0.834

Additional Environmental Impacts

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	C3	C4	D
GWP-GHG ³⁰	kg CO₂-eq.	11.8	12.3	0.00215	0.0163	0.152	0.0163	-4.18
PM	Disease incidence	5.13E-07	5.32E-07	1.17E-10	2.79E-10	7.51E-09	5.68E-10	-4.82E-08
IRP ³¹	kBq U-235-eq.	0.124	0.127	5.48E-08	5.56E-06	2.90E-05	4.24E-04	0.102
ETP-fw ²⁹	CTUe	24.8	26.2	0.00725	0.0878	0.316	0.0708	-1.27
HTP-c ²⁹	CTUh	2.18E-09	2.27E-09	1.22E-13	1.48E-12	1.42E-11	8.39E-12	-1.82E-09
HTP-nc ²⁹	CTUh	2.75E-07	2.83E-07	7.60E-12	5.88E-11	4.72E-10	8.45E-10	-5.97E-08
SQP ²⁹	dimensionless	5.12	8.35	6.63E-05	6.17E-04	0.212	0.0185	0.531

Resource use

Parameter	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	СЗ	C4	D
PERE	MJ	7.59	8.88	9.43E-05	0.00107	0.356	0.0195	2.66
PERM	MJ	0	0	0	0	0	0	0
PERT	MJ	7.59	8.88	9.43E-05	0.00107	0.356	0.0195	2.66
PENRE	MJ	123	128	0.0289	0.219	1.66	0.239	-39.4
PENRM	MJ	0.992	1.01	0	0	0	0	0
PENRT	MJ	124	129	0.0289	0.219	1.66	0.239	-39.4
SM	kg	0.445	0.452	0	0	0	0	0
RSF	MJ	0	0	0	0	0	0	0
NRSF	MJ	0	0	0	0	0	0	0
FW	m ³	0.0211	0.0224	2.43E-07	2.09E-06	8.42E-04	3.36E-05	-0.0189

Waste Categories and Output Flows

Parameter	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	СЗ	C4	D
HWD	kg	3.34E-09	1.00E-08	3.13E-14	3.55E-13	5.53E-11	3.60E-11	-3.00E-10
NHWD	kg	0.242	0.254	4.12E-07	5.31E-06	5.17E-04	0.349	0.711
RWD	kg	7.12E-04	7.32E-04	4.23E-10	4.27E-08	2.26E-07	2.88E-06	7.77E-06
CRU	kg	0	0	0	0	0	0	0
MFR	kg	1.47	1.49	0	0	3.13	0	0
MER	kg	0.00566	0.00575	0	0	0	0	0
EEE	MJ	0	0	0	0	0	0	0
EET	MJ	0	0	0	0	0	0	0

End of Life			Biogenic Carbon Content			
Parameter	Unit	Total		Unit	A1-A3	A1-A3 incl.
Steel collected separately	kg	3.13	-			rollforming
Steel collected with mixed construction waste	kg	0.348	Biogenic carbon content in product	kg C	0	0
Recovery for re-use	kg	0	Biogenic carbon content in packaging	kg C	0.00464	0.0337
Recovery for recycling	kg	3.13	Note: 1 kg biogenic carbon is equivalen	t to 44/12	kg CO₂	
Recovery for energy recovery	kg	0	-			
Disposal to landfill	kg	0.348	-			
Assumptions for scenario	-	n/a	-			

Additional Results for 1 m² of COLORBOND[®] Coolmax[®] steel in 0.42mm base metal thickness (BMT)

In accordance to EN 15804:2012+A1:2013

Environmental Impacts

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	C3	C4	D
GWP	kg CO₂-eq.	11.7	12.1	0.00214	0.0163	0.151	0.0160	-4.13
ODP	kg CFC11-eq.	7.91E-12	8.82E-12	2.03E-16	1.95E-15	8.03E-13	2.60E-14	7.87E-14
AP	kg SO₂-eq.	0.0343	0.0357	7.18E-06	3.00E-05	6.30E-04	4.26E-05	-0.00395
EP	kg PO₄³eq.	0.00336	0.00353	1.67E-06	6.52E-06	5.68E-05	4.55E-06	-1.08E-04
POCP	kg ethene-eq.	0.00504	0.00519	7.09E-07	-7.96E-06	3.38E-05	3.98E-06	-0.00186
ADPE	kg Sb-eq.	3.02E-05	3.08E-05	2.66E-11	2.98E-10	1.29E-08	1.19E-09	-2.12E-07
ADPF	MJ	120	125	0.0289	0.218	1.65	0.230	-40.4

Additional Green Star v1.3 Indicators

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	C3	C4	D
HTPc	CTUh	3.26E-10	3.42E-10	3.30E-15	4.54E-14	5.49E-12	7.34E-13	7.64E-11
HTPnc	CTUh	1.25E-10	3.89E-10	1.58E-15	1.02E-14	1.75E-13	1.71E-14	2.13E-12
LU	kg C deficit-eq.	2.00	2.21	5.47E-06	4.23E-05	0.0172	0.00162	0.222
RDW	m³-eq.	0.00927	0.0100	1.56E-07	1.33E-06	5.60E-04	1.69E-05	-0.0103
IR	kBq U235-eq.	0.123	0.126	5.48E-08	5.56E-06	2.90E-05	4.24E-04	0.102
PM	kg PM2.5-eq.	0.00270	0.00280	5.16E-07	1.40E-06	4.13E-05	3.00E-06	-3.11E-04

29. The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high or as there is limited experience with the indicator.

30. This indicator includes all greenhouse gases included in GWP-total but excludes biogenic carbon dioxide emissions and uptake and biogenic carbon stored in the product as defined by the IPCC AR5 report (IPCC 2013). As this indicator uses the same charaterisation factors as the GWP indicator required in v3.01 of the General Programme Instructions (GPI) of the International EPD[®] System, its inclusion creates comparability with EPDs based on other Product Category Rules (PCRs) aligned with v3.01 of the GPI, as well as comparability with other GHG reporting according ISO 14067.

31. This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and some construction materials, is also not measured by this indicator.



Results for 1 m² of COLORBOND[®] Coolmax[®] steel in 0.48mm base material thickness (BMT)

In accordance to EN 15804:2012+A2:2019

Product mass: 3.95 kg/m² flat

Note: Results for 'A1-A3 incl. rollforming' are for one square metre (1 m²) of flat product. The profile of the rollformed roofing product will affect how many flat square metres are required to cover a given surface area.

Environmental Impacts

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	СЗ	C4	D
GWP-total	kg CO₂-eq.	13.3	13.7	0.00247	0.0188	0.174	0.0192	-4.90
GWP-fossil	kg CO₂-eq.	13.3	13.8	0.00247	0.0187	0.174	0.0191	-4.90
GWP-biogenic	kg CO₂-eq.	-0.00981	-0.112	2.44E-07	6.25E-06	1.94E-04	3.77E-05	0.00285
GWP-luluc	kg CO₂-eq.	4.86E-04	9.64E-04	1.79E-08	2.02E-07	6.68E-06	1.15E-05	-1.00E-04
ODP	kg CFC-11-eq.	7.13E-12	7.95E-12	1.96E-16	1.88E-15	7.74E-13	2.51E-14	7.59E-14
AP	mol H⁺-eq.	0.0466	0.0485	1.17E-05	4.84E-05	8.75E-04	6.03E-05	-0.00488
EP-freshwater	kg P-eq.	3.49E-06	4.76E-06	4.34E-10	3.08E-09	9.51E-08	1.47E-08	-8.75E-07
EP-marine	kg N-eq.	0.0103	0.0107	5.67E-06	2.19E-05	1.88E-04	1.47E-05	-3.70E-04
EP-terrestrial	mol N-eq.	0.115	0.120	6.21E-05	2.40E-04	0.00205	1.61E-04	1.38E-04
POCP	kg NMVOC-eq.	0.0344	0.0359	1.59E-05	4.67E-05	5.20E-04	4.65E-05	-0.00346
ADP-minerals & metals ³²	kg Sb-eq.	3.03E-05	3.08E-05	3.02E-11	3.38E-10	1.46E-08	1.33E-09	-2.47E-07
ADP-fossil ³²	MJ	135	141	0.0328	0.249	1.88	0.271	-44.4
WDP ³²	m ³ world-eq. deprived	0.831	0.899	1.83E-05	1.19E-04	0.0681	0.00130	-0.941

Additional Environmental Impacts

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	C3	C4	D
GWP-GHG ³³	kg CO₂-eq.	13.0	13.5	0.00244	0.0186	0.173	0.0185	-4.72
PM	Disease incidence	5.68E-07	5.88E-07	1.33E-10	3.17E-10	8.53E-09	6.45E-10	-5.47E-08
IRP ³⁴	kBq U-235-eq.	0.126	0.129	6.22E-08	6.31E-06	3.29E-05	4.82E-04	0.115
ETP-fw ³²	CTUe	26.3	27.9	0.00824	0.0997	0.359	0.0804	-1.45
HTP-c ³²	CTUh	2.28E-09	2.37E-09	1.38E-13	1.68E-12	1.61E-11	9.53E-12	-2.06E-09
HTP-nc ³²	CTUh	3.00E-07	3.08E-07	8.63E-12	6.68E-11	5.36E-10	9.59E-10	-6.74E-08
SQP ³²	dimensionless	5.42	9.07	7.53E-05	7.01E-04	0.241	0.0211	0.598

Resource use

Parameter	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	СЗ	C4	D
PERE	MJ	7.90	9.35	1.07E-04	0.00121	0.405	0.0221	3.00
PERM	MJ	0	0	0	0	0	0	0
PERT	MJ	7.90	9.35	1.07E-04	0.00121	0.405	0.0221	3.00
PENRE	MJ	134	140	0.0328	0.249	1.88	0.271	-44.4
PENRM	MJ	0.992	1.01	0	0	0	0	0
PENRT	MJ	135	141	0.0328	0.249	1.88	0.271	-44.4
SM	kg	0.536	0.545	0	0	0	0	0
RSF	MJ	0	0	0	0	0	0	0
NRSF	MJ	0	0	0	0	0	0	0
FW	m ³	0.0220	0.0235	2.76E-07	2.37E-06	9.57E-04	3.82E-05	-0.0213

Waste Categories and Output Flows

Parameter	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	C3	C4	D
HWD	kg	3.55E-09	1.12E-08	3.56E-14	4.03E-13	6.29E-11	4.09E-11	-3.40E-10
NHWD	kg	0.247	0.259	4.68E-07	6.03E-06	5.87E-04	0.396	0.792
RWD	kg	7.23E-04	7.44E-04	4.80E-10	4.85E-08	2.57E-07	3.27E-06	8.68E-06
CRU	kg	0	0	0	0	0	0	0
MFR	kg	1.67	1.70	0	0	3.56	0	0
MER	kg	0.00566	0.00575	0	0	0	0	0
EEE	MJ	0	0	0	0	0	0	0
EET	MJ	0	0	0	0	0	0	0

End of Life			Biogenic Carbon Content			
Parameter	Unit	Total		Unit	A1-A3	A1-A3 incl.
Steel collected separately	kg	3.56	-			rollforming
Steel collected with mixed construction waste	kg	0.395	Biogenic carbon content in product	kg C	0	0
Recovery for re-use	kg	0	Biogenic carbon content in packaging	kg C	0.00464	0.0376
Recovery for recycling	kg	3.56	Note: 1 kg biogenic carbon is equivalen	t to 44/12	kg CO₂	
Recovery for energy recovery	kg	0	-			
Disposal to landfill	kg	0.395	-			
Assumptions for scenario	-	n/a	-			

Additional Results for 1 m² of COLORBOND[®] Coolmax[®] steel in 0.48mm base metal thickness (BMT)

In accordance to EN 15804:2012+A1:2013

Environmental Impacts

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	C3	C4	D
GWP	kg CO₂-eq.	12.9	13.3	0.00243	0.0185	0.172	0.0181	-4.66
ODP	kg CFC11-eq.	8.41E-12	9.42E-12	2.31E-16	2.21E-15	9.11E-13	2.96E-14	8.76E-14
AP	kg SO ₂ -eq.	0.0376	0.0391	8.16E-06	3.40E-05	7.16E-04	4.84E-05	-0.00447
EP	kg PO₄³eq.	0.00369	0.00388	1.90E-06	7.40E-06	6.45E-05	5.16E-06	-1.24E-04
POCP	kg ethene-eq.	0.00561	0.00577	8.05E-07	-9.04E-06	3.83E-05	4.52E-06	-0.00210
ADPE	kg Sb-eq.	3.03E-05	3.08E-05	3.02E-11	3.38E-10	1.46E-08	1.35E-09	-2.39E-07
ADPF	MJ	132	137	0.0328	0.248	1.87	0.262	-45.6

Additional Green Star v1.3 Indicators

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	C3	C4	D
HTPc	CTUh	3.34E-10	3.52E-10	3.74E-15	5.16E-14	6.23E-12	8.33E-13	8.62E-11
HTPnc	CTUh	1.30E-10	4.29E-10	1.79E-15	1.16E-14	1.99E-13	1.94E-14	2.40E-12
LU	kg C deficit-eq.	2.14	2.36	6.21E-06	4.81E-05	0.0196	0.00184	0.250
RDW	m³-eq.	0.00986	0.0107	1.78E-07	1.51E-06	6.36E-04	1.92E-05	-0.0116
IR	kBq U235-eq.	0.125	0.128	6.22E-08	6.31E-06	3.29E-05	4.82E-04	0.115
PM	kg PM2.5-eq.	0.00298	0.00309	5.86E-07	1.59E-06	4.69E-05	3.41E-06	-3.52E-04

32. The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high or as there is limited experience with the indicator.

33. This indicator includes all greenhouse gases included in GWP-total but excludes biogenic carbon dioxide emissions and uptake and biogenic carbon stored in the product as defined by the IPCC AR5 report (IPCC 2013). As this indicator uses the same charaterisation factors as the GWP indicator required in v3.01 of the General Programme Instructions (GPI) of the International EPD* System, its inclusion creates comparability with EPDs based on other Product Category Rules (PCRs) aligned with v3.01 of the GPI, as well as comparability with other GHG reporting according ISO 14067.

34. This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and some construction materials, is also not measured by this indicator.



Results for 1 m² of COLORBOND[®] Coolmax[®] steel in 0.55mm base material thickness (BMT)

In accordance to EN 15804:2012+A2:2019

Product mass: 4.50 kg/m² flat

Note: Results for 'A1-A3 incl. rollforming' are for one square metre (1 m²) of flat product. The profile of the rollformed roofing product will affect how many flat square metres are required to cover a given surface area.

Environmental Impacts

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	C3	C4	D
GWP-total	kg CO₂-eq.	14.7	15.2	0.00281	0.0214	0.199	0.0218	-5.55
GWP-fossil	kg CO₂-eq.	14.8	15.3	0.00281	0.0214	0.198	0.0218	-5.55
GWP-biogenic	kg CO₂-eq.	-0.00937	-0.126	2.79E-07	7.12E-06	2.22E-04	4.30E-05	0.00322
GWP-luluc	kg CO₂-eq.	5.07E-04	0.00105	2.04E-08	2.30E-07	7.61E-06	1.31E-05	-1.14E-04
ODP	kg CFC-11-eq.	7.62E-12	8.54E-12	2.23E-16	2.14E-15	8.82E-13	2.86E-14	8.50E-14
AP	mol H⁺-eq.	0.0513	0.0534	1.34E-05	5.51E-05	9.97E-04	6.87E-05	-0.00555
EP-freshwater	kg P-eq.	3.70E-06	5.14E-06	4.94E-10	3.51E-09	1.08E-07	1.67E-08	-9.91E-07
EP-marine	kg N-eq.	0.0113	0.0118	6.46E-06	2.49E-05	2.14E-04	1.67E-05	-4.25E-04
EP-terrestrial	mol N-eq.	0.127	0.133	7.08E-05	2.74E-04	0.00233	1.84E-04	9.03E-05
POCP	kg NMVOC-eq.	0.0380	0.0397	1.81E-05	5.32E-05	5.93E-04	5.30E-05	-0.00394
ADP-minerals & metals ³⁵	kg Sb-eq.	3.03E-05	3.09E-05	3.44E-11	3.85E-10	1.66E-08	1.52E-09	-2.80E-07
ADP-fossil ³⁵	MJ	149	155	0.0374	0.283	2.14	0.309	-50.3
WDP ³⁵	m ³ world-eq. deprived	0.894	0.970	2.09E-05	1.35E-04	0.0775	0.00148	-1.07

Additional Environmental Impacts

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	СЗ	C4	D
GWP-GHG ³⁶	kg CO₂-eq.	14.4	15.0	0.00278	0.0212	0.197	0.0211	-5.34
PM	Disease incidence	6.31E-07	6.54E-07	1.51E-10	3.61E-10	9.71E-09	7.35E-10	-6.23E-08
IRP ³⁷	kBq U-235-eq.	0.128	0.131	7.09E-08	7.19E-06	3.75E-05	5.49E-04	0.130
ETP-fw ³⁵	CTUe	28.1	29.8	0.00938	0.114	0.409	0.0916	-1.64
HTP-c ³⁵	CTUh	2.39E-09	2.49E-09	1.57E-13	1.92E-12	1.83E-11	1.09E-11	-2.33E-09
HTP-nc³⁵	CTUh	3.29E-07	3.39E-07	9.83E-12	7.61E-11	6.11E-10	1.09E-09	-7.63E-08
SQP ³⁵	dimensionless	5.76	9.92	8.58E-05	7.99E-04	0.274	0.0240	0.677

Resource use

Parameter	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	СЗ	C4	D
PERE	MJ	8.27	9.91	1.22E-04	0.00138	0.461	0.0252	3.40
PERM	MJ	0	0	0	0	0	0	0
PERT	MJ	8.27	9.91	1.22E-04	0.00138	0.461	0.0252	3.40
PENRE	MJ	148	154	0.0374	0.283	2.14	0.309	-50.3
PENRM	MJ	0.992	1.01	0	0	0	0	0
PENRT	MJ	149	155	0.0374	0.283	2.14	0.309	-50.3
SM	kg	0.643	0.653	0	0	0	0	0
RSF	MJ	0	0	0	0	0	0	0
NRSF	MJ	0	0	0	0	0	0	0
FW	m ³	0.0232	0.0249	3.14E-07	2.70E-06	0.00109	4.35E-05	-0.0241

Waste Categories and Output Flows

Parameter	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	C3	C4	D
HWD	kg	3.80E-09	1.25E-08	4.05E-14	4.60E-13	7.16E-11	4.66E-11	-3.86E-10
NHWD	kg	0.252	0.266	5.34E-07	6.87E-06	6.69E-04	0.451	0.886
RWD	kg	7.35E-04	7.59E-04	5.47E-10	5.53E-08	2.92E-07	3.72E-06	9.73E-06
CRU	kg	0	0	0	0	0	0	0
MFR	kg	1.90	1.93	0	0	4.06	0	0
MER	kg	0.00566	0.00575	0	0	0	0	0
EEE	MJ	0	0	0	0	0	0	0
EET	MJ	0	0	0	0	0	0	0

End of Life			Biogenic Carbon Content				
Parameter	Unit	Total		Unit	A1-A3	A1-A3 incl.	
Steel collected separately	kg	4.06	-			rollforming	
Steel collected with mixed construction waste	kg	0.450	Biogenic carbon content in product	kg C	0	0	
Recovery for re-use	kg	0	Biogenic carbon content in packaging	kg C	0.00464	0.0422	
Recovery for recycling	kg	4.06	Note: 1 kg biogenic carbon is equivalent to 44/12 kg CO ₂				
Recovery for energy recovery	kg	0	-				
Disposal to landfill	kg	0.450	-				
Assumptions for scenario	-	n/a	-				

Additional Results for 1 m² of COLORBOND[®] Coolmax[®] steel in 0.55mm base metal thickness (BMT)

In accordance to EN 15804:2012+A1:2013

Environmental Impacts

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	C3	C4	D
GWP	kg CO₂-eq.	14.3	14.8	0.00277	0.0211	0.195	0.0207	-5.28
ODP	kg CFC11-eq.	8.98E-12	1.01E-11	2.63E-16	2.52E-15	1.04E-12	3.37E-14	9.81E-14
AP	kg SO₂-eq.	0.0414	0.0431	9.29E-06	3.88E-05	8.15E-04	5.51E-05	-0.00508
EP	kg PO₄³eq.	0.00407	0.00428	2.16E-06	8.43E-06	7.35E-05	5.88E-06	-1.43E-04
POCP	kg ethene-eq.	0.00626	0.00644	9.17E-07	-1.03E-05	4.37E-05	5.14E-06	-0.00238
ADPE	kg Sb-eq.	3.03E-05	3.09E-05	3.44E-11	3.85E-10	1.66E-08	1.54E-09	-2.71E-07
ADPF	MJ	146	152	0.0373	0.283	2.13	0.298	-51.7

Additional Green Star v1.3 Indicators

Indicator	Unit	A1-A3	A1-A3 incl. rollforming	C1	C2	C3	C4	D
HTPc	CTUh	3.44E-10	3.64E-10	4.27E-15	5.88E-14	7.10E-12	9.49E-13	9.76E-11
HTPnc	CTUh	1.36E-10	4.76E-10	2.04E-15	1.32E-14	2.26E-13	2.21E-14	2.71E-12
LU	kg C deficit-eq.	2.29	2.55	7.08E-06	5.48E-05	0.0223	0.00209	0.283
RDW	m³-eq.	0.0105	0.0115	2.02E-07	1.72E-06	7.24E-04	2.19E-05	-0.0132
IR	kBq U235-eq.	0.127	0.130	7.09E-08	7.19E-06	3.75E-05	5.49E-04	0.130
PM	kg PM2.5-eq.	0.00331	0.00343	6.67E-07	1.82E-06	5.35E-05	3.88E-06	-4.00E-04

35. The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high or as there is limited experience with the indicator.

36. This indicator includes all greenhouse gases included in GWP-total but excludes biogenic carbon dioxide emissions and uptake and biogenic carbon stored in the product as defined by the IPCC AR5 report (IPCC 2013). As this indicator uses the same charaterisation factors as the GWP indicator required in v3.01 of the General Programme Instructions (GPI) of the International EPD* System, its inclusion creates comparability with EPDs based on other Product Category Rules (PCRs) aligned with v3.01 of the GPI, as well as comparability with other GHG reporting according ISO 14067.

37. This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and some construction materials, is also not measured by this indicator.



Interpretation of Results

Impact Category Results

The majority of production (A1-A3) impacts arise from the combustion of fossil fuels, either directly or in the upstream production of electricity and materials. The upstream production of Hot Rolled Coil steel substrate was the most significant contributor to most environmental impact indicators, and the base metal thickness (BMT) has significant influence on their results due to the dominance of the manufacturing of the steel substrate. This emphasises the importance of selecting the appropriate BMT for the intended application; where a thicker steel sheet does not contribute to structural integrity, a lighterweight version of COLORBOND® Coolmax® steel (CMX) with a lower BMT should be considered.

The upstream production of metal coating alloys – a combination of aluminium, zinc and magnesium applied to the steel substrate for corrosion protection – was the most significant contributor to ADP-minerals & metals, IRP, and SQP, and also contributed significantly to most indicators.

Rollforming generally adds less than 5% to total impacts, but has significant impact for EP-freshwater, ODP, WDP, and SQP. These impacts were driven by the upstream production of electricity and cardboard used by rollformers.

Assumption of average product – Sensitivity of results

When similar products are manufactured on different production lines, there is sometimes variation in results. Should production scheduling change significantly, this may be reflected in changes in the calculated impacts. The reason for these differences is the different mix of production routes that contribute to each product. Where products are preferentially made at different locations, the differences are most evident. While unlikely, should production scheduling change significantly, this may be reflected in changes in the calculated impacts. The variation in impact across production lines for COLORBOND® Coolmax® steel (CMX) (flat product) is well under 10%.

Environmental Product Declaration

COLORBOND® Coolmax® steel

References

AS 1397:2021, Continuous hot-dip metallic coated steel sheet and strip - Coatings of zinc and zinc alloyed with aluminium and magnesium.

AS/NZS 2728:2013, Prefinished/pre painted sheet metal products for interior/exterior building applications – Performance requirements.

EN 15804:2012+A1:2013, Sustainability of construction works – Environmental product declarations – Core rules for the product category of construction products

EN 15804:2012+A2:2019, Sustainability of construction works – Environmental product declarations – Core rules for the product category of construction products

General Programme Instructions for the International EPD® System, Version 3.01.

Instructions of the EPD Australasia Programme, Version 3.0.

ISO 14001:2015, Environmental management systems-Requirements with guidance for use

ISO 14021:2016, Environmental labels and declarations – Selfdeclared environmental claims (Type II environmental labelling)

ISO 14025:2006, Environmental labels and declarations – Type III environmental declarations – Principles and procedures

National Waste Report 2020, Pickin J et al., A report prepared for the Department of Agriculture, Water and the Environment by Blue Environment Pty Ltd, 4 November 2020, https://www. dcceew.gov.au/environment/protection/waste/national-wastereports/2020

PCR 2012:01, Construction Products and Construction Services, Version 2.32, 2020.07.01

PCR 2019:14, Construction Products, Version 1.11, 2021-02-05

Sphera, GaBi LCA Database Documentation, 2020, https://www.gabi-software.com/support/gabi/gabi-database-2022-lci-documentation/

For further reference

EPD Owner	BlueScope Steel Limited steeldirect@bluescopesteel.com
LCA Author	BlueScope Steel Limited steeldirect@bluescopesteel.com thinkstep-anz.com info@thinkstep-anz.com
Programme Operator	EPD Australasia Limited info@epd-australasia.com
Product Website	steel.com.au
BlueScope Awards and Certificates (ISO 14001, Worldsteel Climate Action Programme)	bluescope.com/sustainable- steel/awards-and-certificates/
ResponsibleSteel™ certification for Port Kembla Steelworks	bluescope.com/sustainable- steel/responsiblesteel/
BlueScope Sustainability Reporting	bluescope.com/sustainable- steel/reports/

Cover image: Stockland Hervey Bay, Hervey Bay QLD, which uses COLORBOND® Coolmax® steel in the colour Whitehaven®. Architect: PDT Architects. COLORBOND®, Coolmax®, Intramax®, Activate®, CORSTRIP®, TRUECORE®, ZINCALUME®, XLERPLATE®, BlueScope, the BlueScope brand mark and ® colour names are registered trade marks of BlueScope Steel Limited.



For further information, contact BlueScope Steel Direct 1800 800 789

steel.com.au

BlueScope Steel Limited Level 11, 120 Collins St, Melbourne VIC 3000, Australia ABN 16 000 011 058

bluescope.com

